

MDS.02.00

HT-625

SELF LUBRICATED SLIDING BEARINGS



Sliding Layer	Supporting Shell
Special Coating. Treatment "Duritex ML". Colour Grey.	C 0.10 % Max Mn 0.05 % Max Cr 20 - 23 % Ni Rest Mo 8 - 10 % Co 1 % Max Nb 3.15 - 4.15 %

Characteristics	
Working surface acceptable specific static pressure	Max 200 N/mm ²
Working surface acceptable specific dynamic pressure	Max 100 N/mm ²
Maximum sliding speed (dry)	0,50 m/s (100 fpm)
Working temperature	From -200°C to +430° C
Friction factor (dry)	From 0.07 to 0.13

Sliding Surface
HT-625 sliding bearings can be used with or without lubrication. For the applications where the lubrication can only be periodic grease must be adopted. Where the lubrication can be continuous a lubricant oil can be chosen.
Shaft
For proper bushing performance we suggest having a shaft roughness of 0.40µm Max.
Items
The HT-625 can be supplied as many technical items, between them we indicate the followings: <ul style="list-style-type: none"> • Trust Washers • Plain Bearings according to ISO 3547 or according to customer's design drawing • Plain Strips • Special Parts



Follow Us!

#HimonBearings

Note: Information present in this sheet is considered reliable, but conditions and methods of use, which are beyond our control, may modify result. The information and data contained in this data sheet are the result of lengthy and detailed research, however Himon Bearings Srl cannot be held responsible for any incorrect or incomplete data. Owing to the constant development of the products, we reserve the right to make changes to the products without prior notice.